

SUPERTUF PLUS

Supertuf Plus ropes are manufactured from a high strength PE/PP blend. A perfect mooring line for large vessels, these ropes have a high strength to weight ratio, float and do not absorb water. Additionally, they have high resistance to abrasion and chemicals.

Supertuf Plus ropes are easily spliced using a standard tuck splice. Its torque free braided construction provides easy handling and prevents kinks and hockles.

Features & Benefits

- Floats
- Good strength to weight
- Excellent abrasion resistance
- Torque free
- Easy splicing

Applications

- Floating mooring lines for barges/vessels
- Floating winch lines
- Lashings

Type approved product



Nominal Diameter		Size (circ in.)	Approximate Weight		Minimum Tensile Strength Spliced Rope		Minimum Tensile Strength ISO Unspliced Rope	
inch	mm		lbs/100ft	kg/100m	lbs	MT (tonnes)	lbs	MT (tonnes)
3/4	18	2-1/4	10	15	13,691	6.2	15,212	6.9
1	24	3	17	26	24,405	11.1	27,117	12.3
DNV Type Approved Sizes								
1-5/8	40	5	48	72	65,477	29.7	72,752	33.0
1-3/4	44	5-1/2	61	90	78,374	35.6	87,082	39.5
2	48	6	70	104	91,766	41.6	101,963	46.3
2-1/8	52	6-1/2	82	122	105,953	48.1	117,726	53.4
2-1/4	56	7	95	142	120,636	54.7	134,040	60.8
2-1/2	60	7-1/2	110	163	137,699	62.5	152,999	69.4
2-5/8	64	8	124	185	156,846	71.5	174,274	79.1
2-3/4	68	8-1/2	141	209	177,084	80.3	196,761	89.3
3	72	9	157	234	196,231	89.0	218,035	98.9


Tensile Strengths are determined in accordance with Cordage Institute 1500, Test Methods for Fiber Rope. Weights are calculated at linear density under standard preload (200d2) plus 4%. See reverse side for application and safety information.

Technical Information

Specific gravity	0.92*
Melting point	329°F (165°C)
Critical temp.	140°F (60°C)
Coefficient of friction	0.16–0.018*
Elongation at break	15–20%
Fiber water absorption	0–1%
UV resistance	moderate
Wet abrasion	moderate
Dry abrasion	moderate

* value based on data supplied by the fiber manufacturer for new, dry fiber

Supertuf Plus Elongation (%)



SUPERTUF PLUS

Rope Specifications

Minimum Tensile Strength Minimum tensile strengths shown are for new (unused) rope and will decrease after use. All tests are performed in accordance with Cordage Institute Standard CI 1500-2. The rope strength will be reduced after use due to heat, abrasion, ultraviolet or chemical exposure. The tensile strengths may be further reduced by up to 50% as a result of knots or kinks. Minimum tensile strengths are defined as two standard deviations (typical about 10%) below the average.

Maximum Working Loads Maximum working loads are determined by dividing the tensile strength by the safety factor. The safety factor is a function of the physical properties of the rope, the age and history of the rope, the type of service it will be subjected to and the risks involved if failure occurs. For a rope manufacturer to give blanket working load recommendations would be like a car manufacturer giving the "safe driving speed" of their cars. Obviously the conditions of use far outweigh the design characteristics of the rope. Typically safety factors vary from 3:1 (for new rope used in applications with uniform loading and where failure would cause little or no risk to equipment or personnel) to 20:1 (for conditions involving moderate shock loading, possibility of snags or kinks or where failure could cause severe risk to equipment or personnel).

Rope Weights Rope weights shown are average and may vary plus or minus 5%.

Working Elongation Working elongation is shown from a preload tension of 200 times the diameter squared per the Cordage Institute Standard.

Special Requirements

Factory Splicing Various types are available for all of our ropes. Splices can be provided with various types of chafe protection or coatings.

Custom Lengths Special constructions are available on request.

Rope Terminations Cortland International can provide custom terminations such as thimbles, links, rings and custom hardware. Terminations are available in plastic, bronze, stainless steel and galvanized steel. Please call, or email your requirements to contact@cortlandinternational.com for a quotation.

Special Coatings Coatings such as polyurethane, polyethylene and vinylesters may be applied to any of the synthetic ropes to improve snag resistance, sunlight resistance or for color coding. Cortland can provide ropes with a variety of finishes to meet your needs.

Commercial and Military Specifications Certificates of compliance are supplied at no charge if requested when placing the order. Certified test reports can be provided at an additional charge when requested at the time of the order.